




DynaGlas® SolarSoft™ Max

Corrugated Polycarbonate with Highest Daily Light Integral (DLI) & Guaranteed Condensate Control



Overview

DynaGlas SolarSoft Max is a revolutionary breakthrough in the horticultural industry. It is the first corrugated polycarbonate greenhouse covering to be tested for hemispherical light transmission by world renowned Wageningen UR (University and Research Center).

Compared to flat coverings, DynaGlas SolarSoft Max's Greca style corrugation allows excellent light transmittance at low sun angles, while maintaining hemispherical light transmittance up to 78%. Combining this corrugation with a unique proprietary formulation allows the DynaGlas SolarSoft Max sheet to provide 90% light dispersion while maintaining 90% light transmission. This results in a deeper penetration of light that is evenly dispersed into the plant canopy for more consistent crop growth.

These benefits make DynaGlas SolarSoft Max the ultimate solution for greenhouse roofing.

www.PalramAmericas.com

Main Benefits

- Corrugated profile and improved formula allows up to 6% more light into the greenhouse in comparison to other diffused and clear polycarbonate greenhouse coverings
- Up to 90% light transmission
- Up to 90% haze value
- Blocks out UV & far IR radiation
- Virtually unbreakable
- UV2 available (UV protection on both sides)
- Flexible and easy to install
- Wide service temperature range -40° F to +212° F (-40° C to +120° C)
- Highest DLI value of any diffused polycarbonate sheet in the industry.
- DynaGlas SolarSoft Max's white color allows for maximum light transmission while eliminating shadows and reducing unwanted solar heat gain.
- Anti-condensate coating on the underside of the sheet controls disease and plant loss by preventing falling water droplets and reduced light transmission issues.
- 5-year hail and 10-year limited warranty against loss of light transmission / yellowing and condensation control.




More Light. More Often.

The light measurement most growers rely on is the Daily Light Integral (DLI) which indicates the daily amount of accumulated Photosynthetic Active Radiation (PAR). There are many factors that affect the amount of light penetration such as greenhouse structural members, internal obstructions, directional orientation of greenhouse, angle of sun and time of year.

Of these, the angle of incidence of the sun to the greenhouse canopy surface plays a very large part in the overall PAR light transmission into the greenhouse. When the sun is at its lowest point in the sky at sunrise and sunset, flat greenhouse canopies reflect more light than they transmit. So while glass may transmit an extra 1% of light while the sun is at its highest, *it will reflect most of the light as the sun sets lower. Corrugated polycarbonate refracts light at low angles, reduces reflection, and facilitates more light penetration into the greenhouse than any other material.*

This graph, based on data from Wageningen UR, the global leader in greenhouse coverings testing, compares 0.8mm corrugated polycarbonate to standard 4mm greenhouse glass, the two most common long-term greenhouse covering materials.



As the graph depicts:


- At direct sunlight impact angles, the glass and corrugated polycarbonate display similar light transmission
- At low sunlight angles, the corrugated polycarbonate transmits almost 20% more light.

More Evenly Dispersed.

Structural elements can establish shadows and clear glazing can form a direct light impact that may damage plants. Palram's DynaGlas SolarSoft Max utilizes a proprietary formulation to create the perfect balance of evenly dispersed light throughout the plant canopy, while providing an ideal growing environment without the increased risk of plant burn due to intense light beams. Efficiencies are gained by using less water and loading more plants. Diffused light also reduces heat buildup in the greenhouse, resulting in a more pleasant work environment.

Standard Profile & Dimensions

Profile	Color	Width (inches)	Thickness (inches)
Solar Soft	Clear with a light diffusing texture	49.6" or 73.6"	0.048"



* Minimum order requirements may apply.

Regulatory Code Compliance Certification

Organization	Standard	Classification
NRC-CNRC	Canadian NBC 2015 (Canopy Covering)	CCMC Evaluation Report 13450-R
Miami Dade County	FBC 2017 (Canopy Covering)	NOA# 15-1207.08
ICC (International Code Council)	IBC 2015 (Light Transmitting Plastics)	ESR-1893
City of Los Angeles	LABC 2017 (Light Transmitting Plastics)	RR 25298

Definitions:

PAR (Photosynthetic Active Radiation) is intensity of the portion of the light spectrum between 400 nm and 700 nm. This is the light a plant needs for photosynthesis to occur.

Photosynthetic Photon Flux Density (PPFD) is a measurement unit for the amount of photons that reach the plant leaf over a 1 square meter area every second, and is indicated in micromoles or (μmol) per square meter (m^2) per second (s^{-1}), or: **$\mu\text{mol}\cdot\text{m}^{-2}\cdot\text{s}^{-1}$ of PAR.**

DLI is the measurement of **PAR** in **$\mu\text{mol}\cdot\text{m}^{-2}\cdot\text{s}^{-1}$** accumulated over the course of a 24 hour period.



PALRAM AMERICAS
 9735 Commerce Circle
 Kutztown, PA, 19530 USA
 Tel: 800.999.9459
 palramamericas@palram.com



Authorized Distributor

F3409 05.28.19 PBW 86849

In as much as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

